

# Nomex<sup>®</sup> Essential Arc HiCal

Introducing to the Nomex<sup>®</sup> portfolio, a brand new, innovative and lightweight fabric developed for workers exposed to arc flash hazards: Nomex<sup>®</sup> Essential Arc HiCal can provide an impressive ATPV of 12 cal/cm<sup>2</sup> in a single 6.5 oz/yd<sup>2</sup> layer.

In addition, multi-layered solutions with Nomex<sup>®</sup> Essential Arc HiCal are capable of achieving arc ratings exceeding 40 cal/cm<sup>2</sup> to meet the high performance requirements needed by electrical workers.

Nomex<sup>®</sup> Essential Arc HiCal helps deliver enhanced protection and comfort needed to take on tough jobs.

## Extreme protection



Arc flash protection along with heat and flame resistance



Inherent protection; can't be washed out or worn away



Resists tears and abrasion



Extremely durable and long-lasting protective solutions

## Color

Refer to fabric sample for true color representation.



Navy

## Weight

6.5 oz/yd<sup>2</sup> 220gsm (twill)

## Fiber blend

Nomex<sup>®</sup>, Kevlar<sup>®</sup>, modacrylic, antistatic fiber

## Hazards



Arc flash

## Certifications

Nomex<sup>®</sup> fabric solutions are certified to meet the listed standards.\*

ASTM F1506

NFPA 2112

CGSB 155.20\*\*

ISO 11612

NFPA 70E

\*Certifications for the fabrics vary by region. Contact a DuPont representative for additional details.

\*\*Certification pending.

Fabric protection performance

Property	Standard	Units/description	Nomex® Essential Arc HiCal
Fabric construction	—	—	Twill weave
Basis weight	—	oz/yd² (g/m²)	6.5 (220)
(Arc Thermal Performance Value [ATPV])	ASTM F1959 IEC 61482-1-1	cal/cm²	12
Box test	IEC 61482-1-2	Rating	Class 1

Typical physical properties (ASTM, NFPA)

Property	Standard	Units/description	Nomex® Essential Arc HiCal
Fabric construction	—	—	Twill weave
Basis weight	ASTM D3776	oz/yd²	6.5
Tensile strength (Grab test)	ASTM D5034	Warp (lbf) Weft (lbf)	183 101
Elmendorf tear	ASTM D1424	Warp (lbf) Weft (lbf)	7 10
Heat transfer performance (HTP)	NFPA 2112 Section 8.2	Spaced (cal/cm²) Contact (cal/cm²)	11 6
Shrinkage after 5 home laundering cycles	AATCC 135	Warp (%) Weft (%)	<3 <3

Typical physical properties (ISO, EN)

Property	Standard	Units/description	Nomex® Essential Arc HiCal
Fabric construction	—	—	Twill weave
Basis weight	ISO 3801	g/m²	220
Tensile strength	ISO 13934-1	Warp (N) Weft (N)	922 535
Tear strength	ISO 13937-2	Warp (N) Weft (N)	35 35
Dimensional stability	ISO 5077	Warp (%) Weft (%)	<3 <3

Suitable to be used for arc flash protection as per NEC, NESC, NFPA 70E and OSHA requirements.



Discover more about DuPont™  
Nomex® Essential Arc HiCal



dpp.dupont.com  
in DuPont Personal Protection

This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience become available. It is the user’s responsibility to determine the level of toxicity and the proper personal protective equipment needed. The information set forth herein reflects laboratory performance of fabrics, not complete garments, under controlled conditions. This information is intended for use by persons having the technical expertise to undertake evaluation under their own specific end-use conditions, at their own discretion and risk. Anyone intending to use this information should first check that the garment selected is suitable for the intended use. The end-user should discontinue use of garment if fabric becomes torn, worn or punctured, to avoid potential chemical exposure. Since conditions of use are beyond our control, DUPONT MAKES NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND ASSUME NO LIABILITY IN CONNECTION WITH ANY USE OF THIS INFORMATION. This information is not intended as a license to operate under or a recommendation to infringe any trademark, patent or technical information of DuPont or other persons covering any material or its use.

© 2024 DuPont. All rights reserved. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. (07/24) DSF24\_2405-0785